



1 Introduction

This classification report defines the classification assigned to « **705 NOSWEAT / 705 NOSTAIN** » (as described by the sponsor) in accordance with the procedure given in EN 13501-1:2007

CLASSIFICATION REPORT OF REACTION TO FIRE PERFORMANCE IN ACCORDANCE WITH EN 13501-1: 2007

Sponsor:	CLIPSO PRODUCTIONS 5, Rue de l'Eglise 68800 VIEUX-THANN FRANCE
Prepared by :	IFTH Avenue Guy de Collongue 69134 ECULLY CEDEX – FRANCE
Notified laboratory N° :	0072
Classification report N° :	N° 12-04646 L
Issue number :	1
Date of issue :	February 6th, 2013

This classification report consists of four pages and may only be used or reproduced in its entirety.

Ce rapport de classement atteste uniquement des caractéristiques de l'échantillon soumis aux essais et ne préjuge pas des caractéristiques de produits similaires. Il ne constitue donc pas une certification de produits au sens de l'article L.115-27 du code de la consommation et de la loi du 3 juin 1994.

CONDITIONS GENERALES : ART 1 - Toutes les demandes d'essai ou d'étude doivent être présentées par écrit. Elles doivent indiquer avec précision : l'identité et l'adresse du demandeur, le nombre, la nature, la dénomination et les références des échantillons soumis, l'objet du travail demandé. ART 2 - Les demandes sont classées dans l'ordre de leur réception et les travaux entrepris dans le même ordre. En cas d'urgence, un travail pourra exceptionnellement être effectué en priorité. Dans ce cas, l'INSTITUT FRANCAIS TEXTILE-HABILEMENT pourra majorer le prix courant que le demandeur est réputé connaître et accepter. ART 3 - Les rapports et observations ne sont valables que pour les échantillons soumis à l'INSTITUT FRANCAIS TEXTILE-HABILEMENT : un témoin pourra être remis au demandeur, muni du sceau de l'INSTITUT FRANCAIS TEXTILE-HABILEMENT et joint au rapport. ART 4 - L'INSTITUT FRANCAIS TEXTILE-HABILEMENT ne peut être tenu responsable des diverses interprétations et de l'usage qui pourrait être faits des rapports et observations. D'autre part, l'utilisation du nom de l'INSTITUT FRANCAIS TEXTILE-HABILEMENT est subordonnée à l'accord préalable et écrit de la direction régionale de l'INSTITUT FRANCAIS TEXTILE-HABILEMENT concernée. ART 5 - La partie non utilisée des échantillons est conservée pendant une durée d'au moins trois mois à compter de la date du rapport, exception faite des matières ou produits susceptibles de subir une altération. ART 6 - Le règlement des travaux doit être effectué au comptant net sans escompte.

Direction Régionale Rhône-Alpes PACA
Avenue Guy de Collongue ● 69134 ECULLY CEDEX
Tél : (+33) (0)4 72 86 16 00 ● Fax : (+33) (0)4 78 43 39 66
SIRET 433 430 832 00017

2 Details of classified product :

2.1 General :

The product « **705 NOSWEAT / 705 NOSTAIN** » (as described by the sponsor) is defined as stretched ceilings in accordance with EN 14716: 2004.

2.2 Description of the product:

The product « **705 NOSWEAT / 705 NOSTAIN** » (as described by the sponsor), is described below or in the test report provided in support of classification listed in 3.1 :

100 % polyester knitting coated with polyurethane fireproofed in the mass and fluoride resin, for stretched ceiling.

Nominal surface weight: 250 g/m²

Nominal thickness: 0.3 mm

Colour: white

3 This reports and test results in support of classification:

3.1 Test reports :

Name of Laboratory	Name of Sponsor	Test report N°	Test method
IFTH Avenue Guy de Collongue 69134 ECULLY Cedex FRANCE	CLIPSO PRODUCTIONS 5, Rue de l'Eglise 68800 VIEUX-THANN FRANCE	N° 12-04646 dated February 1 st , 2013	NF EN ISO 11925-2 : 2002 NF EN 13823 : 2002

3.2 Test results :

Test method	Parameter	Nb. Test	Results	
			Continuous parameter mean	Compliance parameter
EN ISO 11925-2* Applied on the edge Time exposure : 30 s	Fs < 150mm in 60s	6	/	IN ACCORDANCE
	Ignition of paper		/	NO
EN 13823**	FIGRA _{0.2MJ} (w/s)	3	0	/
	FIGRA _{0.4MJ} (w/s)		0	/
	THR ₆₀₀ (MJ)		0.3	/
	LFS		/	NO REACH
	SMOGRA (m ² /s ²)		0	/
TPS _{600s} (m ²)	42.4	/	/	
LDP _{f<10s}	/	/	NO	
LDP _{f>10s}	/	/	NO	

*Specimen tested without substrate

**Specimen fixed on metallic frame with ventilated cavity 80 mm in width behind the sample according to the chapter 4.1.1.3-b of the standard EN 14716: 2004, sides the most remote from the angle and the spaces situated behind every wing being left opened.

4 Classification and field of application:

4.1 Reference of classification:

This classification has been carried out in accordance with EN 13501-1:2007

4.2 Classification :

The product « **705 NOSWEAT / 705 NOSTAIN** », in relation to fire behaviour is classified: **B**

The additional classification in relation to smoke product is: **s 1**

The additional classification in relation to flaming droplets / particles is: **d 0**

The format of the reaction to fire classification for construction products excluding flooring is:

Fire Behaviour		Smoke Production		Flaming Droplets
B	-	s	1	- d 0

REACTION TO FIRE CLASSIFICATION : B – s1 – d0

4-3 Field of application:

This classification is valid for the following product parameters :

Composition : 100 % polyester knitting coated with polyurethane fireproofed in the mass and fluoride resin, for stretched ceiling.

Nominal surface weight : 250 g/m²

Nominal thickness : 0.3 mm

Colors : white



This classification is valid for the following end used application:

- Stretched ceilings fixed with gap-air

5 Limitation:

This classification document does not represent type approval or certification of the product.

The test laboratory has played no part in sampling the product for the test, although it holds appropriate references, supplied by the manufacturer, to provide for traceability of the samples tested.

Report	Signatory	Signature*	Date
Prepared by:	Jean-Marc ORAISON Fire Product Manager IFTH		February 6 th , 2013
Authorized by :	Pascal DENIZART Quality manager and Solutions for Enterprises – IFTH		February 6 th , 2013

* For and in the name of **I.F.T.H.**